

PRODUCT DATA

FIVE STAR STRUCTURAL CONCRETE GUNITE WP HIGH STRENGTH, WET PROCESS SHOTCRETE REPAIR

PRODUCT DESCRIPTION

Five Star Structural Concrete Gunite WP is a wet process shotcrete applied, permanent concrete repair material. Five Star Structural Concrete Gunite WP may be used from 1/4 inch (6 mm) to full depth applications and provides a long finishing time. Five Star Structural Concrete Gunite WP provides increased corrosion protection of steel reinforced structures with migrating corrosion inhibitor technology and very low chloride ion permeability.

ADVANTAGES

- Large volume applications
- Versatile 1/4 inch (6 mm) to full depth applications
- Long finishing time
- Very low chloride ion permeability
- Pneumatically applied
- Excellent freeze/thaw resistance
- Low rebound
- Available in 3000 lb bulk bag packaging for large volume applications
- Outstanding corrosion resistance for protection and rehabilitation

USES

- Vertical and overhead repairs
- Structural repair for industrial plants
- Repair of load bearing walls, ceilings and other structural members
- Marine and hydraulic structure repair

PACKAGING AND YIELD

Five Star Structural Concrete Gunite WP is packaged in heavy-duty polyethylene lined bags and is available in 50 lb. (22.7 kg) units yielding approximately 0.39 cubic feet (11.0 liters) at maximum water. Five Star Structural Concrete Gunite WP is also available in 3,000 lb (1,360 kg) bulk sacks for large volume applications.

SHELF LIFE

One year in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

PLACEMENT GUIDELINES

1. SURFACE PREPARATION: All surfaces in contact with Five Star Structural Concrete Gunite WP shall be free of oil, grease, laitance,

TYPICAL PROPERTIES @ 70°F (21°C)

Compressive Strength, ASTM C 109

- 1 Day 3,500 psi (24.2 MPa)
- 28 Days 8,000 psi (55.2 MPa)

Compressive Strength, ASTM C 42 in accordance with ACI 506R-90

- 3 Days 6,000 psi (41.4 MPa)
- 7 Days 7,500 psi (51.8 MPa)
- 28 Days 8,500 psi (58.7 MPa)

Bond Strength, ASTM C 882

- 7 Days 2,000 psi (13.8 MPa)

Thermal Coefficient of Expansion, ASTM C 531

5.0 × 10⁻⁶ in/in/°F
(9.0 × 10⁻⁶ mm/mm/°C)

Chloride Ion Permeability, ASTM C 1202

- 28 Days Very Low (<1,000 Coulombs)

Working Time at 70°F (21°C)

30 minutes

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown may result. Test methods are modified where applicable.

and other contaminants. Concrete must be clean, sound and rough to ensure a good bond. Mechanically roughen concrete surfaces in accordance with ICRI Technical guideline 03732 to a minimum concrete surface profile roughness (CSP) 6 or greater. A perimeter edge and minimum depth of 1/4 inch (6 mm) should be provided for a durable repair. Feather edging is not desirable. Soak concrete surfaces prior to application with liberal quantities of potable water, leaving the concrete saturated and free of standing water. Surfaces shall be conditioned to between 45°F and 90°F (7°C and 32°C) at the time of placement.

2. MIXING: Wet down mortar mixer (stationary barrel with moving blades) before using and drain any excess water. A drill and paddle mixer is acceptable for single bag mixes. Add the minimum amount of premeasured potable water (2¼ quarts per 50 lb. unit) as stated on product packaging to mixer. While mixing, slowly add Five Star Structural Concrete Gunite WP and mix to a uniform consistency for three to four minutes. To achieve desired consistency for wet process application, add remaining

FIVE STAR STRUCTURAL CONCRETE GUNITE WP

HIGH STRENGTH, WET PROCESS SHOTCRETE REPAIR

water as necessary. Do not exceed maximum water content as stated on product packaging or add an amount that will cause segregation. Mix thoroughly for approximately five minutes. Do not mix more material than can be placed within 30 minutes. Do not retemper the mix by adding additional water.

3. **METHODS OF PLACEMENT:** Apply Five Star Structural Concrete Gunitite WP to full design thickness whenever possible. Repair material is applied in layers just thick enough to prevent sagging. Direct nozzle perpendicular to surface and rotate in a series of circular patterns, filling inside corners first. Five Star Structural Concrete Gunitite WP should emerge from the nozzle in a uniform, uninterrupted flow. Finish to desired texture with screed, float, trowel, or brush. To obtain optimum results, repair shall be installed to full depth without allowing intermediate lifts to harden. Where placement depth and patch geometry require installation in lifts, subsequent lifts may be placed after repair material has reached initial set. Applied material shall be given a raked finish to ensure proper adhesion between lifts. Repair material must be kept continuously wet from time of hardening until installation of succeeding lifts. For more detailed application and curing procedures, refer to ACI 506R-90, Guide to Shotcrete Report.

SPECIAL CONDITIONS: For use in cold temperatures, Five Star Structural Concrete Gunitite WP must be maintained at a temperature of at least 45°F (7°C). Protect from freezing until a compressive strength of at least 1,000 psi (6.9 MPa) is obtained. Faster strength gain will occur when the Five Star Structural Concrete Gunitite WP and mixing water have been conditioned to a higher temperature prior to placement. In high temperatures, Five Star Structural Concrete Gunitite WP should be kept as cool as possible, but not exceeding 90°F (32°C). Ice cold water should be used for mixing to help maintain sufficient working time.

4. **POST-PLACEMENT PROCEDURES:** Five Star Structural Concrete Gunitite WP shall be coated with an approved curing compound meeting the water retention properties of ASTM C 309 immediately after finishing. Protect from excessive evaporation prior to set.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Design-A-Spec™ installation guidelines or call Stonhard at (800) 263.3112.

CONSIDERATIONS

- Never exceed the maximum water content as stated on the package or mix to a consistency which will cause segregation.
- Temperature of surfaces must be between 45°F and 90°F (7°C and 32°C) at time of placement. For cold and hot weather placement, call Stonhard at (800) 263.3112.
- Repair material shall be protected from freezing until it reaches 1,000 psi (6.9 MPa).
- Placement shall be continuous to avoid cold joints.

CAUTION

Contains cementitious material and crystalline silica. International Agency for Research on Cancer has determined that there is sufficient evidence for the carcinogenicity of inhaled crystalline silica to humans. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. PRIOR TO USE, REFER TO SAFETY DATA SHEET.

For worldwide availability, additional product information and technical support, contact your local sales representative, or call Stonhard at (800) 263.3112.

SKU / PRODUCT CODE	DESCRIPTION	UNIT SIZE
29426	Five Star Structural Concrete Gunitite WP	50 lb. Bag

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Important:

Stonhard Construction Solutions believes the information contained here to be true and accurate as of the date of publication. Stonhard Construction Solutions makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 11/11

