

PRODUCT DATA

STONDECK XDI RIGID SLAB ON GRADE DECKING SYSTEM

PRODUCT DESCRIPTION

StonDeck XDI is a rigid car park deck coating system which provides a colourful, waterproof wearing surface for indoor covered slab on grade areas where moisture is not a concern.

USES/APPLICATIONS

StonDeck XDI cosmetically enhances and reduces noise, provides lighter, safer environments to visit. StonDeck XDI is suitable for refurbishment of existing decks and on new construction projects.

BENEFITS

- Waterproof - Protects from chlorides
- Aesthetically attractive – brightens up dull, dark, musty car parks
- Reduces noise – stops tire squeal
- Hard wearing – abrasion resistant
- Solvent free
- Fire resistant
- Slip resistant
- Excellent bond strength

MODEL SPECIFICATION

Product: StonDeck XDI – Interior Rigid Deck System

Finish: Gloss

Thickness: 60 mils (with texture)

SYSTEM COMPONENTS

StonDeck Epoxy Primer

A two-component, epoxy primer to hold the broadcast aggregate and provide system thickness.

StonDeck Aggregate

A high-wear graded quartz aggregate broadcast to provide an abrasion, slip and wear resistant surface.

*System durability can be upgraded by substituting for emeraldum or aluminum oxide aggregates.

StonDeck Topcoat

A two component low viscosity and low flexibility sealer to seal the broadcast aggregate.

ADDITIONAL COMPONENTS (IF REQUIRED)

StonDeck Primer

A range of two component, low viscosity epoxy primers to provide a strong, secure bond on damp and poor quality substrates.

PHYSICAL CHARACTERISTICS

The figures that follow are typical properties achieved in laboratory tests at 20°C (68°F) and at 50% Relative Humidity.

Slip Resistance ASTM F1679	Dry 1.20 Wet 0.95
Temperature Resistance	Softens over 70°C, hardens on cooling
Water Permeability	Nil - Karsten test (impermeable)
Chemical Resistance	Resistant to gasoline, oil, diesel, antifreeze hydraulic fluid, chlorides and battery acids
Abrasion Resistance	Taber Abrader: 40 mg loss per 1000 cycles (1 kg load using H-22 wheels)
Bond Strength ASTM D4541	Greater than cohesive strength of 3600 psi (25 N/mm ²) concrete >275 psi (1.9 MPa)
Fire Resistance BS476 Part 3 (2004)	Designated EXT.FAA (Extended Fire Exposure Roof Test) • No fire penetration within 1 hour • No spread of flame

SUBSTRATE REQUIREMENTS

Concrete substrate should be a minimum of 25 MPa, sound and free from laitance, dust, oils, and other contamination. Substrate should be dry to 80% Relative Humidity. (See Primers for damp/ poor substrates.)

PACKAGING

StonDeck XDI is conveniently packaged as detailed below for easy handling.

StonDeck Primer

(2) units of standard primer. Additional primers are available for poor quality and damp substrates. See separate data sheets.

Broadcast Aggregate

30 lb bags of quartz broadcast aggregate.*

(approx. 150 sq. ft./bag)

*(Can be substituted with aluminum oxide or emeraldum for higher abrasion resistance)

StonDeck Topcoat

(2) 4.2 gallon pails of StonDeck Finish Resin.

(approx. 60 sq. ft./ gallon at 27 mils over texture)

STONDECK XD1

RIGID SLAB ON GRADE DECKING SYSTEM

STORAGE CONDITIONS

Store all components between 60°F to 77°F / 16°C to 25°C in a dry area. Keep out of direct sunlight. Avoid excessive heat and do not freeze.

COLOUR

StonDeck XD1 is available in 8 standard colours. Refer to the StonDeck colour sheet. Custom colours are available upon request with extended lead times.

SPEED OF CURE

	10°C	20°C	30°C
Light Traffic	30 Hours	16 Hours	10 Hours
Full Traffic	36 Hours	24 Hours	16 Hours
Full Chemical Cure	12 Days	7 Days	5 Days

CLEANING AND MAINTENANCE

For best performance clean regularly using a single or double rotary scrubber drier in conjunction with a mildly alkaline detergent.

ENVIRONMENTAL CONSIDERATIONS

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environment and health considerations are controlled during manufacture and application of the products by Stonhard staff and fully trained and experienced contractors.

SUBSTRATE

Proper preparation is critical to ensure an adequate bond. The substrate must be dry and free of all wax, grease, oils fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles must be removed by mechanical methods, i.e., abrasive blasting or scarifying. Other contaminant's may be removed by scrubbing with a heavy-duty industrial detergent (Stonkleen TD9) and rinsing with clean water. The surface must show open pores throughout and have a sandpaper texture. For recommendations or additional information regarding a range of substrate priming and preparation options, contact Stonhard's Technical Service Department.

ADDITIONAL PRIMING (AS REQUIRED)

StonDeck Primers are available for poor quality and damp substrates when required. The primer must be fully cured and the concrete must be completely sealed off prior to the application of the membrane. For recommendations or additional information regarding substrate priming, contact Stonhard's Technical Service Department.

POT LIFE

After mixing, the StonDeck components will have a working time of approximately 10 – 15 minutes. The working time varies greatly depending upon temperature.

APPLYING

Application of the StonDeck system is accomplished as follows;

1. StonDeck Standard Epoxy Primer is mixed and applied immediately to the floor. The material is distributed using nap rollers and after 5 minutes maximum, aggregate is broadcasted until refusal into the wet primer. Allow to cure then remove excess aggregate.
2. StonDeck Finish is mixed and applied to seal the aggregate. The material is distributed using nap rollers. Ensure an even coat of approximately 8–10 mils is applied to fully seal the broadcast aggregate.

Refer to StonDeck XD1 Directions for further details.

RECOMMENDATIONS

- DO NOT attempt to install material if the StonDeck XD1 components are not within 60 to 77°F / 16 to 25°C
- DO NOT use water or steam in the vicinity of the application.
- The use of suitable protective clothing, gloves and safety glasses must be worn during mixing and application of the product.
- Avoid Contact! In case of contact with eyes, rinse immediately with copious amounts of water and seek medical attention. In case of contact with skin, clean immediately with water and soap.

NOTES

- Safety Data Sheets for StonDeck XD1 products are available upon request.
- A staff of Technical Service Engineers is available to assist with installation or to answer questions related to Stonhard Construction Solutions Decking products.
- Requests for technical service or literature can be made through local sales representatives and offices or corporate offices located worldwide.

Important:

Stonhard Construction Solutions believes the information contained here to be true and accurate as of the date of publication. Stonhard Construction Solutions makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

11/15

Rev. 02/20